

shall be cured for at least seven (7) days either by covering it with at least one (1) inch of wet sand which shall be kept wet by sprinkling with water, or by ponding.

MISCELLANEOUS

23. Court Lines

a. The necessary court lines shall be one and one-half (1-1/2) inches in width and shall be marked as indicated. All lines shall be formed by painting with two coats of a good portland cement paint.

Note: White lines are standard and are usually preferred regardless of the color of the court. They may also be built integrally into the slab with white portland cement concrete as described in the accompanying article.

24. Grading Around Court

a. The ground around the court for a distance of three (3) feet from the court limits shall be graded up level with the court surface, using clay or earth firmly compacted.

25. Color

a. If it is deemed desirable to incorporate color in the concrete placed above the reinforcing, it shall be placed in the mixer with the other materials in the quantities specified. Only mineral oxide pigments shall be used and in no case shall more than ten (10) per cent of color by weight of the cement be added.

(End of Specification)